JOURNAL OF DENTAL RESEARCH

1998 • Volume 77 • Special Issue B • Abstracts of Papers

76th General Session of the IADR

Held in conjunction with the British, Continental European, Irish, and Israeli Divisions of the IADR and the Scandinavian Association for Dental Research

June 24-27, 1998, Nice, France

1998 PROGRAM

International Association for Dental Research



76th General Session & Exhibition of the IADR

Held in conjunction with the British, Continental European, Irish, and Israeli Divisions of the IADR and the Scandinavian Association for Dental Research

June 24-27, 1998

New Dual Cure, Multipurpose, Adhesive Resin Cement.
B. ZALSMAN*, H. DODIUK, A. VALDMAN and I. EPPELBAUM
(B.J.M Laboratories Ltd., RAFAEL Armament Development Authority)

At B.J.M Laboratories Ltd. an investigation related to a new adhesive resin cement designated High-Q-Bond (HQB) was carried out.

The objective of the study was aimed at developing a new dental cement which is characterized by superior adhesion to dentin, enamel, precious and non precious cast alloys, porcelain, acrylics and amalgam. Furthermore, the newly developed adhesive composition was designed to be simple to use. When bonding to cast alloys no primers are necessary. Since the cement is dual cured, it can also be used to veneer alloys. When bonding orthodontic brackets, etching of the enamel is not necessary. Thus, upon removal of the bracket, no damage is caused to the enamel surface. HQB is comprised of acrylic multifunctional monomers, coupling agents containing both hydrophilic and hydrophobic groups, which provide high shear bond strength, sufficiently high durability and high bio-compatibility. The system also contains a variety of fillers responsible for the high compressive and hardness properties. The shear bond strength was measured using the Bencor Multi-T system (Danville Engineering Inc.). The force required to fracture the samples was determined using a Lloid mechanical tester (model LR10K, Lloid instruments Ltd.). Each cement or metal cylinder was placed under continuous loading at 5 mm per minute until fracture occurred. The shear bond strength measured to 50 micron grit blasted Ni-Cr-Be metal (Rexillium III) was 45.2±5.7 (S.D.) MPa, to 600 grit polished Rexillium III 29.2±6.9 MPa, and to unetched enamel 15.6±4.7 MPa. The control group Panavia 21 (Kuraray America Inc.) gave 45.6±7.1 MPa 12.8±4.9 MPa and 10.9±2.8 MPa respectively. The results of this study indicate that the HOB adhesive resin cement has the potential to be an easy to use and effective adhesive resin cement. However its clinical performance is still to be determined.